

Ab-initio determination of the localized/delocalized f -manifold in UPd₂Al₃

L. Petit¹, A. Svane¹, W.M. Temmerman², Z. Szotek², and R. Tyer^{2,3}

¹ *Institute of Physics and Astronomy, University of Aarhus,
DK-8000 Aarhus C, Denmark*

² *Daresbury Laboratory, Daresbury, Warrington WA4 4AD, UK*

³ *Department of Physics and Astronomy, University of Sheffield, Sheffield, S3 7RH, UK*

(February 2, 2008)

Abstract

The electronic structure of UPd₂Al₃ is described using the self-interaction corrected local-spin-density approximation to density functional theory. The groundstate is found to be characterized by the coexistence of localized (f^2) and delocalized U f electrons, in agreement with experimental evidence. We observe significant difference in electronic structure between UPd₂Al₃ and the previously studied UPt₃ compound. Even though a trend towards localization exists in UPt₃, the total energies and the density of states at the Fermi level favor a groundstate with localized f^1 , rather than f^2 U ions.

PACS 71.27.+a, 71.20.Gj, 71.15.Nc

Heavy fermion (HF) systems are some of the most fascinating condensed matter materials.¹ Their highly correlated electrons give rise to large values of the low temperature specific heat coefficient, γ , which in certain cases is larger than that of a normal metal by more than a factor of 1000. This is associated with highly enhanced effective quasi-particle masses, m^* , of some 1000 times the free electron mass. Recently new insight has been gained into the nature of these heavy quasiparticles in the magnetically ordered heavy fermions UPd₂Al₃ and UPt₃.² This work has established that magnetic order is the prerequisite to formation of these heavy quasiparticles. Specifically, it is asserted that coupling of localized and delocalized 5f electrons lies at the origin of heavy quasiparticles in UPd₂Al₃ and UPt₃.^{2,3}

In the standard description, the large specific heat coefficients can be correlated to a large density of states (DOS) of heavy quasiparticles at the Fermi level, i.e., a narrow resonance at the Fermi level resulting from the interaction of the localized f states with the conduction electrons. In the weak-coupling Kondo limit the atomic moments of the localized states are individually screened by the conduction electrons. With increasing hybridization, coherence sets in, leading to the Fermi liquid of weakly interacting, extremely heavy quasiparticles. However, the heavy fermion state will not form, if the interactions between unscreened or incompletely screened local moments induce a magnetic phase transition, with the onset of magnetic order. This is the case in many rare earth and actinide metals such as e.g. UPd₃. Contrary to this picture, the new observation by Dressel² indicates that for UPd₂Al₃ and UPt₃ the heavy quasiparticles are *only* created by magnetic excitations in the magnetically ordered state, within the manifold of localised and delocalised f states. In the present paper these localised and delocalised states in UPd₂Al₃ are determined from *ab initio* self-interaction corrected (SIC) local spin density (LSD) calculations and discussed in comparison with UPt₃.⁴

In UPd₂Al₃, the specific heat coefficient is $\gamma=140 \text{ mJ mol}^{-1} \text{ K}^{-2}$,⁵ i.e. less extreme than the value for the prototypical heavy fermion compound CeAl₃ ($\gamma=1600 \text{ mJ mol}^{-1} \text{ K}^{-2}$) but still considerably larger than the value for a normal metal such as Pd ($\gamma=9.4 \text{ mJ mol}^{-1} \text{ K}^{-2}$).

At $T_N=14.3$ K, UPd_2Al_3 undergoes an antiferromagnetic phase transition, with a resulting moment of $0.85 \mu_B$ per U-ion. At the critical temperature $T_c=2$ K,⁵ a superconducting phase transition occurs, as indicated by a sharp drop in electrical resistivity, and a large jump in the specific heat.^{5,6} The pronounced magnetic moment is retained below T_c .⁷ From the specific heat measurements,⁶ muon spin rotation measurements,⁸ and neutron scattering studies,⁹ it emerges that superconductivity and anti-ferromagnetism coexist in UPd_2Al_3 . It has been established that magnetic excitations between two f -electrons localized at each site, and the remaining f -electron are causing superconductivity.¹⁰ Recently it has been suggested^{2,3} that the heavy fermion superconductor UPt_3 can be similarly described in terms of a coupling between the localized f^2 configuration and the delocalized f 's.

Applying density functional theory¹¹ (DFT) to such HF compounds is not straightforward. While this theory is formally exact for an arbitrary many-electron system, in its most widely used approximations, like the local spin density or generalized gradient approximation (GGA), it relies on the exchange and correlation effects of a homogeneous electron gas, which is a rather poor reference system for heavy fermion compounds. The LSD scheme has been very successful in describing the cohesive properties of solid state systems with itinerant valence electrons. In the $4f$ and $5f$ systems, however, the band formation competes with a strong tendency towards localization due to large on-site f - f correlations that go beyond the LSD. Therefore, it is not obvious to what extent the results from bandstructure calculations remain valid. Nevertheless, owing to the fact that the $5f$ electrons in the U compounds are considerably less localized than for example the $4f$ electrons in the corresponding rare-earth compounds, LSD is known to provide useful electronic structure in the normal phase of these compounds. For instance, the Fermi surface of UPt_3 is well reproduced by LSD,¹² and for UPd_2Al_3 it was shown^{13,14} that the experimental de Haas van Alphen results, and the measured magnetic moment, could be reproduced by calculations treating all the U f -electrons as itinerant, hybridizing with the conduction electrons. The latter work¹⁴ concluded, however, that in order to explain the very anisotropic magnetic susceptibility of UPd_2Al_3 , one needed to consider the coexistence of two different kinds of

5*f* electrons, i.e., localized and itinerant ones.

The self-interaction-corrected local-spin-density approximation (SIC-LSD),¹⁵ constitutes a scheme capable of treating both localized and delocalized electrons on an equal footing, by including an explicit energy contribution for an electron to localize (the self-interaction correction).¹⁶ This localization energy is the sum of the self-Coulomb and self-exchange-correlation energies of the *f*-state. For an extended state this energy correction vanishes, but for a localized U 5*f*-state the self-interaction correction is of the order of 30 mRy. In the SIC-LSD application to actinide systems,^{4,17} a particular localized f^n configuration is assumed on each actinide ion, while all other degrees of freedom are allowed to form bands, in a self-consistency cycle. The localized states loose their band-formation energy, but gain the self-interaction correction energy which is subtracted from the LSD total energy functional. On balance, comparing different localized f^n scenarios, the global energy minimum establishes which configuration is the groundstate. In the SIC-LSD picture, the localized electrons are no longer available as band-forming valence electrons, and accordingly the valency of the actinide ion may be defined as^{18,19} $N_{val}=Z-N_{core}-N_{semi}-N_{SIC}$, where Z is the atomic number (92 for U), N_{core} is the number of atomic core electrons (78), N_{semi} is the number of semicore electrons (8), and N_{SIC} is the number of localized electrons. Thus, for UPt₃ the SIC-LSD scheme has revealed a groundstate characterized by localized f^1 electron on U (pentavalent configuration), which is intermediate between the itinerant (f^0) behavior in URh₃ and the more localized f^2 U ions found in UPd₃ and UAu₃ (tetravalent configurations).⁴ In the present work a similar study of UPd₂Al₃ is reported. Three configurations have been investigated, assuming respectively localized f^2 , f^1 and f^0 configurations on the U sites.

The SIC-LSD formalism has been implemented^{16,20} within the tight-binding linear muffin-tin orbitals method (LMTO),^{21,22} with the atomic sphere approximation (ASA). All relativistic effects, including spin-orbit interaction, have been incorporated in the Hamiltonian. For UPd₂Al₃ two separate energy panels have been used, one for the U 6*s* and 6*p* semi-core states, and one for the valence electrons. Apart from the 4*d*, 5*s* and 5*p* orbitals on the Pd

atom, and the $3s$, $3p$, and $3d$ orbitals on the Al atom, the valence panel has comprised the $7s$, $6d$ and $5f$ orbitals on the U atom with the $7p$ degrees of freedom treated by downfolding.²²

In figure 1 we show the results of the total energy calculations as a function of volume for respectively the hexavalent (f^0), pentavalent (f^1), and tetravalent (f^2) configurations, with the f^0 simply corresponding to the standard LSD approximation. The tetravalent groundstate configuration is seen to give the lowest total energy, in agreement with the U^{4+} configuration predicted by experiment. The global minimum occurs at a volume of 681 au³, in good agreement with the measured value, $V_{exp}=700$ au³. The minima for the f^0 and f^1 configurations are shifted slightly to lower volumes, as the partial pressure of itinerant f -electrons is negative. The exact values of the minimum volumes depend somewhat on the ratio of atomic spheres adopted in the ASA, but the relative ordering of the minima is preserved, i.e., the finding of the ground state as f^2 is robust in this respect. The present calculations use the fixed ratio of atomic spheres as $R_U : R_{Pd} : R_{Al} = 3.4 : 2.4 : 2.5$.

With two of the f -electrons localized in the tetravalent configuration, the DOS of UPd_2Al_3 around the Fermi level differs considerably from the corresponding DOS in the LSD configuration, as shown in Fig. 2. Thus, in the itinerant scenario, with all f -electrons delocalized (Fig. 2a), we obtain a relatively large partial f -DOS (dotted line) at the Fermi level of about 102 states/Ry, as compared to the f^2 configuration with only 20 states/Ry (Fig. 2b). In the latter configuration, most of the f weight has been transferred into the two localized states, and the remaining delocalized f -states hybridize with the s , p and d levels on the neighbouring Al and Pd sites. This strong hybridization between f -electrons and conduction electrons which is observed in both the tetravalent and delocalized¹³ configurations, can explain the fact that the measured specific heat coefficient is only about 140 mJ mol⁻¹ K⁻² in UPd_2Al_3 , i.e., we are dealing with moderately heavy itinerant electrons at the Fermi level. Despite this qualitative agreement, we must however not forget that by allowing an f -electron to delocalize the corresponding strong on-site f - f correlations are ignored, and that we therefore might considerably overestimate the effect of f -conduction electron band-formation. The effect of these correlations becomes clear when we compare the

calculated and experimental values for the specific heat coefficient. Here, in the tetravalent configuration we obtain $\gamma=12 \text{ mJ mol}^{-1} \text{ K}^{-2}$, i.e. too small by a factor of 10 with respect to experiment. The same discrepancy between calculation and measurement has been observed in other heavy fermion compounds,^{23,12} the reason being that although the correlations are actually not strong enough to localize the f -electrons, they lead to a considerable narrowing of the hybridized f pd -band, resulting in a specific heat coefficient that is enhanced with respect to the LSD calculations by a factor of up to 20-30.^{23,24} Thus we do expect to find too small a value for γ , and the fact that LSD value is in better agreement ($\gamma_{LSD}=23 \text{ mJ mol}^{-1} \text{ K}^{-2}$) with experiment is a result of the increased f -weight at the Fermi level due to the delocalization of the f -electrons, rather than an indication of a better description of the electronic structure in terms of narrow bands.

There are now strong indications that, in UPd_2Al_3 , the existence of two localized f -electrons is the prerequisite for the appearance of superconductivity and heavy quasiparticles.^{2,10,25-27} The argument is that the itinerant heavy quasiparticles are strongly coupled to the localized f electrons, and interact effectively with each other by the intermediary of magnetic excitations. It has been suggested that the superconductivity in UPt_3 might be of similar origin.² Optical conductivity measurements by these authors show a pronounced pseudogap in the low temperature response, in both UPd_2Al_3 and UPt_3 , which they relate to magnetic correlations between localized and delocalized f -electrons. Zwicknagl *et al.*³ have shown that treating two of the f -electrons in UPt_3 as localized in LDA band-structure calculations, may reproduce the observed de Haas-van Alpen frequencies, and that the interaction between itinerant and localized f -electrons may lead to mass enhancements of a factor ~ 10 . There are however noticeable differences in the low temperature properties of UPd_2Al_3 and UPt_3 .²⁸ Thus even though antiferromagnetism and superconductivity coexist in UPt_3 below $T_c=0.55 \text{ K}$, the magnetic moment is very small, only $0.02 \mu_B$. Also, unlike in UPd_2Al_3 , in UPt_3 the magnetic moment is affected by the superconducting phase transition.²⁹

The SIC-LSD calculations of UPt_3 ⁴ also find indications in favour of coexisting localized

and delocalized f -electrons. However in those calculations, it is the pentavalent f^1 configuration, rather than the tetravalent f^2 configuration, which turns out to be energetically most favourable. Furthermore, in the pentavalent configuration a narrow f -peak is pinned to the Fermi level, in agreement with the heavy fermion character of this compound, whilst in the tetravalent configuration the UPt_3 DOS at the Fermi energy vanishes, as is shown in Fig. 3. In fact, according to the present SIC-LSD calculations, in the scenario with two localized f -electrons, UPt_3 becomes very similar to UPd_3 , which is then difficult to reconcile with experimental evidence,³⁰ since UPd_3 is neither a heavy fermion compound nor a superconductor. In UPd_2Al_3 , as can be seen from Fig. 1, the energy difference between the f^2 and f^1 configuration is $E(f^2) - E(f^1) \sim -6$ mRy. For UPt_3 , UPd_3 and UAu_3 the corresponding energy differences are +5 mRy, -5 mRy and -9 mRy, respectively.⁴ Thus with respect to localization, UPd_2Al_3 is quite similar to UPd_3 (tetravalent configuration), and more localized than UPt_3 . Experimental evidence seems to suggest that UPt_3 is close to an antiferromagnetic instability,³⁰ and consequently the f -electrons are situated at the borderline of a localization/delocalization transition. In our SIC-LSD calculations for UPt_3 , this instability is reflected by a groundstate configuration with one extra delocalized f -electron as compared to UPd_2Al_3 . However, correlations of this extra delocalized electron are most likely not adequately accounted for by the LSD approximation, and would plausibly need to be described in a theory involving fluctuating f^1 and f^2 configurations, such as the dynamical coherent potential approximation.³¹ In particular, the nearly vanishing magnetic moment observed for UPt_3 is not reproduced in the SIC-LSD approach. The SIC-LSD results indicate however that it is energetically not favourable to statically localize two f electrons. Hence, the quasiparticle model of Zwicknagl *et al.*³ might possibly still be valid for UPt_3 , although it seems to be more straightforwardly applicable to UPd_2Al_3 .

In summary, SIC-LSD total energy and DOS calculations of UPd_2Al_3 have been performed. A ground state of localized U f^2 shells has been obtained where additionally strongly hybridized states of f character appear at the Fermi level. The SIC-LSD *ab initio* calculations provide direct evidence for the picture of coexisting localized and delocalized

f -electrons which is inferred from experiments (such as 2) to explain heavy quasiparticles and superconductivity. The calculations do not confirm a similar degree of localization for the f -electrons in UPt_3 and therefore magnetic excitations in UPd_2Al_3 and UPt_3 are most likely to be different.

This work has been partially funded by the Training and Mobility Network on ‘Electronic Structure Calculation of Materials Properties and Processes for Industry and Basic Sciences’ (contract:FMRX-CT98-0178) and the Research Training Network ‘Psi-k f-electron’ (contract:HPRN-CT-2002-00295).

REFERENCES

- ¹ G. R. Stewart, Rev. Mod. Phys. **56**, 755 (1984); H. R. Ott and Z. Fisk, in *Handbook on the Physics and Chemistry of the Actinides*, edited by A. J. Freeman and G. H. Lander (North-Holland, Amsterdam, 1987), p. 85; N. Grewe, and F. Steglich, in *Handbook on the Physics and Chemistry of Rare Earths*, vol. 5, edited by K. A. Gschneidner and L. Eyring (North-Holland, Amsterdam, 1991), p. 343.
- ² M. Dressel, N. Kasper, K. Petukhov, B. Gorshunov, G. Grüner, M. Huth, and H. Adrian, Phys. Rev. Lett. **88**, 186404 (2002).
- ³ G. Zwicknagl, A. N. Yaresko, and P. Fulde, Phys. Rev. B **65**, 081103 (2002).
- ⁴ L. Petit, A. Svane, W. M. Temmerman, and Z. Szotek, Phys. Rev. Lett. **88**, 216403 (2002).
- ⁵ C. Geibel, C. Schank, S. Thies, H. Kitazawa, C. D. Bredl, A. Böhm, M. Rau, A. Grauel, R. Caspary, R. Helfrich, U. Ahlheim, G. Weber, and F. Steglich, Z. Phys. B - Condensed Matter **84**, 1 (1991).
- ⁶ R. Caspary, P. Hellmann, M. Keller, G. Sparn, C. Wassilew, R. Köhler, C. Geibel, C. Schank, F. Steglich, and N. E. Phillips, Phys. Rev. Lett. **71**, 2146 (1993).
- ⁷ A. Krimmel, P. Fischer, B. Roessli, H. Maletta, C. Geibel, C. Schank, A. Grauel, A. Loidl, and F. Steglich, Z. Phys. B - Condensed Matter **86**, 161 (1992).
- ⁸ R. Feyerherm, A. Amato, F. N. Gygax, A. Schenk, C. Geibel, F. Steglich, N. Sato, and T. Komatsubara, Phys. Rev. Lett. **73**, 1849 (1994).
- ⁹ T. E. Mason, G. Aeppli, Mat. Fys. Medd. Dan. Vid. Selsk. **45**, 231 (1996).
- ¹⁰ N. K. Sato, N. Aso, K. Miyake, R. Shiina, P. Thalmeier, G. Varelogiannis, C. Geibel, F. Steglich, P. Fulde, and T. Komatsubara, Nature (London) **410**, 340 (2001).
- ¹¹ P. Hohenberg, and W. Kohn, Phys. Rev. **136**, B864 (1964); W. Kohn and L. J. Sham, Phys. Rev. A **140**, 1133 (1965).

- ¹² R. C. Albers, A. M. Boring, and N. E. Christensen, Phys. Rev. B **33**, 8116 (1986).
- ¹³ L. M. Sandratskii, J. Kübler, P. Zahn, and I. Mertig, Phys. Rev. B **50**, 15834 (1994).
- ¹⁴ K. Knöpfle, A. Mavromaras, L. M. Sandratskii, and J. Kübler, J. Phys.: Condens. Matter **8**, 901 (1996).
- ¹⁵ A. Zunger, J. P. Perdew, and G. L. Oliver, Solid State Commun. **34**, 933 (1980); J. P. Perdew and A. Zunger, Phys. Rev. B **23**, 5048 (1981).
- ¹⁶ W. M. Temmerman, A. Svane, Z. Szotek and H. Winter, in *Electronic Density Functional Theory: Recent Progress and New Directions*, edited by J. F. Dobson, G. Vignale and M. P. Das (Plenum, New York, 1998), p. 327.
- ¹⁷ L. Petit, A. Svane, W. M. Temmerman, and Z. Szotek, Phys. Rev. B **63**, 165107 (2001); L. Petit, A. Svane, W. M. Temmerman, and Z. Szotek, Eur. Phys. J. B. **25**, 139 (2002).
- ¹⁸ P. Strange, A. Svane, W. M. Temmerman, Z. Szotek and H. Winter, Nature (London) **399**, 756 (1999).
- ¹⁹ L. Petit, A. Svane, Z. Szotek, P. Strange, H. Winter, and W. M. Temmerman, J. Phys.: Cond. Matt. **13**, 8697 (2001).
- ²⁰ A. Svane, Phys. Rev. B **53**, 4275 (1996).
- ²¹ O. K. Andersen, Phys. Rev. B **12** 3060 (1975).
- ²² O. K. Andersen, O. Jepsen, and D. Glözel, in *Highlights of Condensed Matter Theory*, International School of Physics ‘Enrico Fermi’, Course 89, ed. by F. Bassani, F. Fumi and M. P. Tosi, (North-Holland, Amsterdam, 1985), p 59.
- ²³ M. M. Steiner, R. C. Albers, L. J. Sham, Phys. Rev. Lett. **72**, 2923 (1994).
- ²⁴ E. K. R. Runge, R. C. Albers, N. E. Christensen, and G. E. Zwicknagl, Phys. Rev. B **51**, 10375 (1995).

- ²⁵ N. Sato, N. Aso, B. Roessli, G. H. Lander, T. Komatsubara, Y. Endoh, and O. Sakai, Journal of Alloys and Compounds **271-273**, 433 (1998).
- ²⁶ M. Jourdan, M. Huth, and H. Adrian, Nature (London) **398**, 4 (1999).
- ²⁷ P. Thalmeier, Eur. Phys. J. B **27**, 29 (2002).
- ²⁸ R. H. Heffner, and M. R. Norman, Comments Cond. Mat. Phys. **17**, 361 (1996).
- ²⁹ G. Aeppli, D. Bishop, C. Broholm, K. Siemensmeyer, M. Steiner, and N. Stüsser, Phys. Rev. Lett. **63**, 676 (1989), S. M. Hayden, L. Taillefer, C. Vettier, and J. Flouquet, Phys. Rev. B **46**, 8675 (1992), E. D. Isaacs, P. Zschack, C. L. Broholm, C. Burns, G. Aeppli, A. P. Ramirez, T. T. M. Palstra, R. W. Erwin, N. Stücheli, and E. Bucher, Phys. Rev. Lett. **75**, 1178 (1995).
- ³⁰ A. de Visser, A. Menovsky, and J. J. M. Franse, Physica **147B**, 81 (1987).
- ³¹ Y. Kakehashi, Phys. Rev. B **45**, 7196 (1992); Y. Kakehashi, *ibid.*, **65**, 184420 (2002).

FIGURES

FIG. 1. Total Energy (in Ry/formula unit) versus volume for UPd_2Al_3 . Three scenarios are considered for the U-ion : f^0 (empty circles), f^1 (filled circles), and f^2 (stars). The arrow indicates the value for the experimental volume.

FIG. 2. DOS of UPd_2Al_3 , (a) in the hexavalent configuration, (b) in the tetravalent configuration. The fat solid, dotted, thin solid, and dashed lines correspond, respectively, to the total DOS, the projected U f DOS, the projected Pd d DOS, and the projected Al p DOS. The energy (in Ry) is relative to the Fermi level (energy zero).

FIG. 3. Total DOS of UPt_3 in the tetravalent configuration, which is energetically unfavorable compared to the pentavalent configuration. The energy (in Ry) is relative to the Fermi level (energy zero), which falls in the hybridization induced gap.





